



WF2.5  
WF5.0  
WF10

### CARATTERISTICHE

I **Warmfoam**, composto da una spugna in polietilene da 5 mm, è ideale per tutti i tipi di applicazioni. Grazie al suo spessore e alle caratteristiche del materiale, è estremamente leggero: può quindi essere trasportato comodamente grazie ai rotoli di altezza 1 mt. La spugna in polietilene ha il compito di dare stabilità meccanica al sistema e garantisce l'effetto antirumore e anti calpestio.

| CARATTERISTICHE                 | UNITA'                | PANNELLO |
|---------------------------------|-----------------------|----------|
| SPESSORE                        | mm                    | 5        |
| PESO                            | Kg/m <sup>2</sup>     | 0.030    |
| VALORE                          | m <sup>2</sup> .K.W-1 | 0.19     |
| DENSITA'                        | Kg/m <sup>3</sup>     | 30+/-3   |
| CARICO DI ROTTURA LONGITUDINALE | N/mm <sup>2</sup>     | >0.18    |
| CARICO DI ROTTURA TRASVERSALE   | N/mm <sup>2</sup>     | >0.16    |
| TEMPERATURA DI IMPIEGO          | C°                    | -40/+95  |
| PERMEABILITA' AL VAPORE ACQUEO  | ng/Pa s m             | 0.12     |
| CONDUCIBILITA' TERMICA          | Kcal/h m C°           | 0.0340   |

| MODELLO | AREA (m <sup>2</sup> ) - DIMENSIONI(m) |
|---------|----------------------------------------|
| WF2.56  | 2.5/1X2.5                              |
| WF5.0   | 5.0/1X5                                |
| WF10    | 10/1X10                                |



WF2.5  
WF5.0  
WF10

### CARATTERISTICHE

**Warmfoam**, made of a 5 mm polyethylene foam, is ideal for all types of applications. Thanks to its thickness and material properties, it is extremely lightweight and can therefore be easily transported in 1 m high rolls.

The polyethylene foam provides mechanical stability to the system and ensures effective noise reduction and anti-footfall performance.

| TECHNICAL SPECIFICATIONS   | UNIT                  | PANEL   |
|----------------------------|-----------------------|---------|
| THICKNESS                  | mm                    | 5       |
| WEIGHT                     | Kg/m <sup>2</sup>     | 0.030   |
| VALUE                      | m <sup>2</sup> .K.W-1 | 0.19    |
| DENSITY                    | Kg/m <sup>3</sup>     | 30+/-3  |
| LONGITUDINAL BREAKING LOAD | N/mm <sup>2</sup>     | >0.18   |
| TRANSVERSE BREAKING LOAD   | N/mm <sup>2</sup>     | >0.16   |
| OPERATING TEMPERATURE      | C°                    | -40/+95 |
| WATER VAPOUR PERMEABILITY  | ng/Pa s m             | 0.12    |
| THERMAL CONDUCTIVITY       | Kcal/h m C°           | 0.0340  |

| MODEL  | AREA (m <sup>2</sup> ) - DIMENSIONS (m) |
|--------|-----------------------------------------|
| WF2.56 | 2.5/1X2.5                               |
| WF5.0  | 5.0/1X5                                 |
| WF10   | 10/1X10                                 |